


BEDEGI
Quality Test Laboratory
Compression Report

CUSTOMER : "ბედეგი"
CUSTOMER : ლაბორატორია
ADDRESS 1 : Orxevi
ADDRESS 2 :
BLOCK TYPE : ბორდიური 30 x 15 x 5
 :

DATE : 5/9/2024
RAPOR NO : # 4 / 9.5.2024
STANDARD :
RESERVE 1 :
RESERVE 2 :
RESERVE 3 :

T. NO	WIDTH mm	LENGTH mm	HEIGHT mm	WEIGHT g	DENSITY g/cm3	SAMPLE DATE t1	TEST DATE t2	SAMPLE DAY day	FORCE kN	STRENGTH N/mm2
1	100	300	50	4521	3014.00	29.3.2024	9.5.2024	28+	1194.00	39.80
2	100	300	50	4355	2903.33	29.3.2024	9.5.2024	28+		
3										
4										
5										
6										

AVARAGE
 AVR.3DAY
 AVR.7DAY
 AVR.28DAY



Controler

Renat Begishev